

2130

ProPex 2130 is a polypropylene woven fabric. This engineered geotextile is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non-biodegradable. Polypropylene is stable within a pH range of 2 to 13, making it one of the most stable polymers available for geotextiles today. We wish to advise that **ProPex 2130** meets the following minimum average roll values:

Property	Test Method	Minimum Average Roll Value (English)	Minimum Average Roll Value (Metric)
Grab Tensile	ASTM-D-4632	124x124 lb	0.550x 0.550 kN
Grab Elongation	ASTM-D-4632	15% x 20%	15% x 20 %
Mullen Burst	ASTM-D-3786	300 psi	2060 kPa
Puncture	ASTM-D-4833	65 lb	0.285 kN
Trapezoidal Tear	ASTM-D-4533	65 lb	0.285 kN
UV Resistance	ASTM-D-4355	80 %	80 %
AOS ⁽¹⁾	ASTM-D-4751	30 sieve	0.600 mm
Permittivity	ASTM-D-4491	0.05 sec ⁻¹	0.05 sec ⁻¹
Flow Rate	ASTM-D-4491	10 gal/min/ft ²	405 L/min/m ²

(1) max. average roll values

Amoco Fabrics and Fibers Company manufactures the woven fabric indicated above. The values listed are a result of testing conducted in on-site laboratories. A letter certifying the minimum average roll values will be issued from the manufacturing plant by the Quality Control Manager at the time shipment is made.

DATE ISSUED: 01/02/04

Amoco Fabrics and Fibers Company
 260 The Bluffs
 Austell, GA 30168
 PH: 770-944-4569
 FX: 770-944-4584

Exclusion of Liability

Information contained in this publication is accurate to the best of the knowledge of Amoco Fabrics and Fibers Company. Any information or advice obtained from BP otherwise than by means of this publication and whether relating to BP materials or other materials, is also given in good faith. However, it remains at all times, the responsibility of the customer to ensure that BP materials are suitable for the particular purpose intended. Insofar as materials not manufactured or supplied by BP are used in conjunction with or instead of BP materials, the customer should ensure that he has received from the manufacturer or supplier all the technical data and other information relating to such materials. BP accepts no liability whatsoever (except as otherwise expressly provided by law) arising out of the use of information supplied, the application of processing of the products described herein, the use of other materials in lieu of BP materials in conjunction with such other materials.

